

# MAXIMUM PERFORMANCE SERIES MP531110M UV ADHESIVE

TECHNICAL DATA SHEET TDS #: MP531110M UV Adhesive Passed ISO 10993 Cytotoxicity

#### **DESCRIPTION**

MP531110M is a high performance UV curing adhesive engineered to bond a wide range of plastic, metals, and glass. It can be used in a variety of product assemblies and it promotes innovative design solutions. Our MP531110M has passed ISO 10993 Cytotoxicity testing and it is a leading performer when used for medical device applications. This maximum performance adhesive is tack free and creates an extremely strong, durable bond. During in-line inspection this adhesive flouresces a blue color when using a low intensity black light. This UV adhesive is a fast curing low viscosity product. MP531110M is often cured with an electroless lamp D, medium pressure metal halide lamp. This UV adhesive also works well with UV light emitted diodes (UV LED) at wavelengths of 365 nm to 410 nm. Design engineers select MP531110M for the optimum in finished product quality, reliability, performance, and cost effectiveness. MP5311010M is an essential tool in improving overall product quality, lowering per unit cost, and reducing processing time.

#### PHYSICAL PROPERTIES (CURED):

<b>Durometer Hardness</b>	D70
Water Absorption, 2 hrs. @100 °C	3.6%
Water Absorption, 24 hrs. @ 25 °C	3%
Glass Transition Temperature, °C	65
Tensile Strength PSI	3600
Dielectric Constant	<4
Dielectric Strength, volts/mil	>400
Working Temperature °F	-60 to 300
Flexibility@RT	No
Blue Flourescing	Yes

## PHYSICAL PROPERTIES (UNCURED):

Chemical Class Acrylate
Solvent Content None
Appearance Liquid
Density, g/ml 1.02

Viscosity, 25 °C, 20 RPM 3000cp-5000cp

Flash Point °C 77

## **Benefits**

- Superior Bond Strength
- Solvent Free
- Low Odor
- Improves Finished Product Quality
- Durable
- Good Impact and Vibration Resistance
- Easily Automated
- No Clean Up

#### **Substrate Applications**

Polycarbonate (PC)
Polyvinylchloride (PVC)

Polyethylene, Polypropylene requires surface treat-

ment such as corona, etc.

Metal Glass

### **CURE SCHEDULE**

Medium Pressure Metal Halide Flood Lamp Station @ 50mW/cm2 Fusion F 300 S Lamp D Conveyor @ 20 @ FPM Fixed time between 2 Glass Slides @ low intensity black light Cure Depth @ 50 mW/cm2 for 2 minutes UV LED 365 nm to 410 nm

5 Seconds for 20% UV block PVC Cure depth @ 0.3 inch 0.5 second 1.1 inch Time depends on the intensity and wavelength

## Storage and Shelf Life

This UV Cure material should be stored in a dark place, above 0°C and below 30 °C. The shelf life is one year from the date of manufacture.



Engineering Excellence
For technical information
and support call 1-800-552-0299 or visit our website at

# **Directions for Use**

- 1. This product cures at exposure to daylight. Minimize to expose during storage and handling.
- 2. Surface of substrates should be clean and free from grease, mold release, or other contaminants.
- 3. Cure speed is dependent on UV energy, intensity of UV Light, required depth of cure and percentage of light transmission of substrates.
- 4. For the best performance, Fusion Lamp D or medium pressure metal halide should be used. Also, UVLED at 365 nm to 410 nm can be used.
- 5. Allow cured parts to cool before testing to any service loads.
- 6. Air inhibits a surface cure. To minimize this effect an inert gas such as nitrogen can be used or a higher intensity can be used.