



**Adhesive Systems, Inc.**  
An ISO 9001:2008 Certified Company

# MAXIMUM PERFORMANCE SERIES

## MP531102I

### UV ADHESIVE

**TECHNICAL DATA SHEET**  
**TDS #: MP531102I**  
**UV Adhesive**  
*Passed ISO 10993 Cytotoxicity*

#### DESCRIPTION

**MP531102I** is a high performance UV curing adhesive engineered to bond plastics, metal, and glass. It can be used in a variety of product assemblies and it promotes innovative design solutions. It is a fast cure, strong bonding adhesive. Our MP531102I has passed ISO 10993 Cytotoxicity testing and is a leading performer when used for bonding general industrial applications. MP531102I is often cured with an electroless lamp D, medium pressure metal halide lamp. This UV adhesive also works well with UV light emitted diodes (UV LED) at wavelengths of 365 nm to 410 nm. Design engineers select MP531102I for the optimum in finished product quality, reliability, performance, and cost effectiveness. MP531102I is an essential tool in improving overall product quality, lowering per unit cost, and reducing processing time.

#### PHYSICAL PROPERTIES (UNCURED):

Chemical Class	Acrylate
Solvent Content	None
Appearance	Liquid
Density, g/ml	1.04
Viscosity, 25 °C, 20 RPM	180cp-270cp
Flash Point °C	77

#### PHYSICAL PROPERTIES (CURED):

Durometer Hardness	D70
Water Absorption, 2 hrs. @100 °C	3%
Water Absorption, 24 hrs. @ 25 °C	2.5%
Glass Transition Temperature, °C	65
Tensile Strength PSI	4400
Dielectric Constant	<4
Dielectric Strength, volts/mil	>400
Working Temperature °F	-60 to 300
Flexibility@RT	No
Blue Fluorescing	No

#### CURE SCHEDULE

Medium Pressure Metal Halide Flood Lamp Station @ 50mW/cm2  
Fusion F 300 S Lamp D Conveyor @ 5 FPM  
Fusion F 300 S Lamp D Conveyor @ 10 FPM  
Fusion F 300 S Lamp D Conveyor @ 20 FPM  
Fixed time between 2 Glass Slides @ low intensity black light  
Cure Depth @ 50 mW/cm2 for 2 minutes  
UV LED 365 nm to 410 nm

5 seconds for 20% UV block PVC  
Cure Depth @ 0.8 inch  
Cure Depth @ 0.6 inch  
Cure Depth @ 0.35 inch  
0.5 second  
1.1 inch  
Time depends on the intensity and wavelength

#### Benefits


- Superior Bond Strength
- Solvent Free
- Low Odor
- Improves Finished Product Quality
- Durable
- Good Impact and Vibration Resistance
- Easily Automated
- No Clean Up

#### Substrate Applications

PET  
PVC  
Polyethylene, Polypropylene requires surface treatment such as corona, etc.  
Metal  
Glass

#### Storage and Shelf Life

This UV Cure material should be stored in a dark place, above 0°C and below 30 °C. The shelf life is one year from the date of manufacture.



#### **Engineering Excellence**

For technical information and support call **1-800-552-0299** or visit our website at

**[www.instantca.com](http://www.instantca.com)**

## **Directions for Use**

- 1. This product cures at exposure to daylight. Minimize to expose during storage and handling.**
- 2. Surface of substrates should be clean and free from grease, mold release, or other contaminants.**
- 3. Cure speed is dependent on UV energy, intensity of UV Light, required depth of cure and percentage of light transmission of substrates.**
- 4. For the best performance, Fusion Lamp D or medium pressure metal halide should be used. Also, UVLED at 365 nm to 410 nm can be used.**
- 5. Allow cured parts to cool before testing to any service loads.**
- 6. Air inhibits a surface cure. To minimize this effect an inert gas such as nitrogen can be used or a higher intensity can be used.**

*NON-WARRANTY: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. Adhesive Systems shall not be liable for any injury, loss, or damage in the use of its chemical products since the conditions of use are beyond our control. In every case we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Because of changing reporting requirements and other variables it is impossible to guarantee the accuracy of the information contained in this document. It is the responsibility of the user to determine proper personal protection based on the actual condition of use and to comply with all Federal, State, and Local laws and regulations.*