



Adhesive Systems, Inc.
An ISO 9001:2008 Certified Company

MAXIMUM PERFORMANCE SERIES

MP532088O

UV ADHESIVE

TECHNICAL DATA SHEET
TDS #: MP532088O
UV Adhesive

DESCRIPTION

MP532088O is a high performance UV curing adhesive engineered to bond glass and plastics. It is a flexible dual cure adhesive. This product can be cured under UV light or heat. Our MP532088O is a leading performer when used for bonding optical applications and general industrial applications. MP532088O is often cured with an electroless lamp D, medium pressure metal halide lamp. This UV adhesive also works well with UV light emitted diodes (UV LED) at wavelengths of 365 nm to 395 nm. Heat can be carried out at 120°C for 30 minutes. Design engineers select MP532088O for the optimum in finished product quality, reliability, performance, and cost effectiveness. MP532088O is an essential tool in improving overall product quality, lowering per unit cost, and reducing processing time.

PHYSICAL PROPERTIES (UNCURED):

Chemical Class	Acrylate Solvent
Content	None
Appearance	Colorless Liquid
Density, g/ml	1.04
Viscosity, 25 °C, 20 RPM	1200cp-1800cp
Flash Point °C	103

Benefits

- Superior Bond Strength
- Solvent Free
- Low Odor
- Improves Finished Product Quality
- Durable
- Good Impact and Vibration Resistance
- Easily Automated
- No Clean Up

PHYSICAL PROPERTIES (CURED):

Refractive Index	1.4889
Durometer Hardness	D14
Linear Shrinkage	1.40%
Water Absorption, 2 hrs. @100 °C	2.4%
Water Absorption, 24 hrs. @ 25 °C	2.1%
Glass Transition Temperature, °C	9
Dielectric Constant	<4
Dielectric Strength, volts/mil	>400
Working Temperature °F	-60 to 300
Flexibility@RT	Yes
Blue Fluorescing	None

Substrate Applications

Soft fillings for Glass and PMMA Plastic

CURE SCHEDULE

Medium Pressure Metal Halide Flood Lamp Station @ 50mW/cm2 for two minutes

Fusion F 300 S Lamp D Conveyor @ 5 FPM

Fixed time between 2 Glass Slides @ low intensity black light

UV LED 365 nm to 395 nm

Cure Depth @ 1.8 cm

Cure Depth @ 0.2 cm

11 seconds

Time depends on the intensity and wavelength

Storage and Shelf Life

This UV Cure material should be stored in a dark place, above 0°C and below 30 °C. The shelf life is one year from the date of manufacture.



Engineering Excellence

For technical information and support call **1-800-552-0299** or visit our website at

www.instantca.com

Directions for Use

- 1. This product cures at exposure to daylight. Minimize to expose during storage and handling.**
- 2. Surface of substrates should be clean and free from grease, mold release, or other contaminants.**
- 3. Cure speed is dependent on UV energy, intensity of UV Light, required depth of cure and percentage of light transmission of substrates.**
- 4. For the best performance, Fusion Lamp D or medium pressure metal halide should be used. Also, UVLED at 365 nm to 395 nm can be used.**
- 5. Allow cured parts to cool before testing to any service loads.**
- 6. Air inhibits a surface cure. To minimize this effect an inert gas such as nitrogen can be used or a higher intensity can be used.**

NON-WARRANTY: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. Adhesive Systems shall not be liable for any injury, loss, or damage in the use of its chemical products since the conditions of use are beyond our control. In every case we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Because of changing reporting requirements and other variables it is impossible to guarantee the accuracy of the information contained in this document. It is the responsibility of the user to determine proper personal protection based on the actual condition of use and to comply with all Federal, State, and Local laws and regulations.

Engineering Excellence

For technical information
and support call **1-800-552-0299** or visit our website at

www.instantca.com