

Revised  
June 2002



9411 Corsair Road  
Frankfort, IL 60423  
1-800-552-0299 Phone  
1-815-464-5650 Fax

**EMERGENCY PHONE 1-800-255-3924**  
**TECHNICAL DATA SHEETS**  
**TORQUE 48 RC**

**Description:**

**Torque 48 RC** is a fast curing high strength anaerobic adhesive for locking and sealing threads, and retaining of cylindrical components. Highly resistant to heat, corrosion, vibrations, water, gases, oils, hydrocarbons and many chemicals.

**Properties of Uncured Product:**

Composition	Urethane Methacrylate
Appearance	Green, fluorescent liquid
Specific Gravity (77°F/25°C g/ml)	1.13
Viscosity, Brookfield (77°F/25°C mPa.s)	
Spindle 2- 20 rpm	400 to 600 mPa.s
Flash Point, TCC	>100°C
Shelf life at 20°C	1 year
Storage temperature	8° - 28°C

**HEAT CURE**

Typical heat cure conditions consist of heating and maintaining bondline at a temperature of 40°C and after one hour 100% of strength on steel is achieved.

**CURE SPEED VS. SUBSTRATE**

% Full strength	Steel	Aluminium
25	10 min	1 hrs
50	20 min	8 hrs
100	2-72 hrs	

**CURE SPEED VS. JOINT GAP**

% Full strength	Gap 0,05mm	Gap 0,25mm
25	10 min	6 hrs
50	20 min	15 hrs
100	2-72 hrs	

**CURE SPEED VS. TEMPERATURE**

% Full strength	Temperature	
	5°C	40°C
25	3 hrs	4 min
50	6 hrs	8 min
100	30-72 hrs	50min-72 hrs

**Properties of Cured Product:**

**Functional strength at 24 hrs 20° on steel**

Shear Strength (ISO 10123)	18 to 35 N.m
Shear Strength (DIN 54452)	16 to 30 N.m
Coefficient of thermal expansion (ASTM D696)	80 X 10 <sup>-6</sup> 1/K
Thermal conductivity (ASTM C177)	0., W/Mk
Specific heat	0.3 KJ.Kg <sup>-1</sup> K <sup>-1</sup>
Temperature range	-55° +150°C

**ENVIRONMENTAL RESISTANCE**

**Hot strength at temperature**

Test.Temp. °C	% retained strength
25°	100%
50°	100%
100°	97%
150°	75%

**Heat aging**

Samples aged 3000 hours at indicated temperature and tested at room temperature.

Test temp. °C	% retained strength
180°	30%
150°	100%

**Chemical / Solvent Resistance**

Specimens immersed for 1000 hrs at indicated temperature and tested at room temperature.

	Test Temp. °C	% retained strength
50/50 Water / Glycol	87	75
Unleaded Petrol	22	100
Motor Oil	125	100
Brake Fluid	22	100
Acetone	22	100

**Engineering Excellence**

For technical information  
and support call **1-800-552-0299** or visit our website at

**[www.instantca.com](http://www.instantca.com)**